

Test Report

Report No. : TCT260112C003008

Date : Jan. 20, 2026

Page No.: 1 of 6

Applicant: Shenzhen Shuguan Electronic Technology Co.,Ltd.**Address:** Room 301, Building C, No. 11, Gelan Road, Dahe Community, Guanhu Street, Longhua District, Shenzhen City, Guangdong Province.**The following sample was submitted and identified by/on behalf of the client as:**

Sample Name: SGR/ SIR/SGPD/SGPT/PD/PT/PDA SERIES

Model No.: SGR/ SIR/SGPD/SGPT/PD/PT/PDA SERIES

Manufacturer: Shenzhen Shuguan Electronic Technology Co.,Ltd.

Address: Room 301, Building C, No. 11, Gelan Road, Dahe Community, Guanhu Street, Longhua District, Shenzhen City, Guangdong Province.

Sample Received Date: 2026.01.12

Testing Period: 2026.01.12—2026.01.20

Test Method: Please refer to the following page(s).

Test Result(s): Please refer to the following page(s).


| Test Requested | Conclusion |
|--|------------|
| As specified by client, Disassembly the sample and determine the Lead(Pb), Cadmium(Cd), Mercury(Hg), Hexavalent Chromium(Cr(VI)), Polybrominated Biphenyls(PBBs), Polybrominated Diphenyl Ethers(PBDEs), Bis-(2-ethylhexyl) Phthalate (DEHP), Benzylbutyl Phthalate (BBP), Dibutyl Phthalate (DBP) and Diisobutyl Phthalate(DIBP) content of the parts in accordance with RoHS directive 2011/65/EU and the amendment directive (EU) 2015/863. | Pass |

Checked by



Evan Fang

Approved by



Ryan Zhang

Technical Manager



Test Report

Report No. : TCT260112C003008

Date : Jan. 20, 2026

Page No.: 2 of 6

Test Result(s)

| Part No. | Part Description | Test Item(s) | Result of EDXRF Screening test (1) | Result of Chemical Test (2) (mg/kg) | RoHS Conclusion |
|----------|-------------------------|--------------|------------------------------------|-------------------------------------|-----------------|
| 1 | Black body | Pb | BL | --- | Pass |
| | | Cd | BL | --- | Pass |
| | | Hg | BL | --- | Pass |
| | | Cr(VI) | BL | --- | Pass |
| | | PBBS | IN | N.D. | Pass |
| | | PBDEs | IN | N.D. | Pass |
| | | DBP | --- | N.D. | Pass |
| | | BBP | --- | N.D. | Pass |
| | | DEHP | --- | N.D. | Pass |
| | | DIBP | --- | N.D. | Pass |
| 2 | Silvery color metal pin | Pb | BL | --- | Pass |
| | | Cd | BL | --- | Pass |
| | | Hg | BL | --- | Pass |
| | | Cr(VI) | BL | --- | Pass |
| | | PBBS | --- | --- | NA |
| | | PBDEs | --- | --- | NA |
| | | DBP | --- | --- | NA |
| | | BBP | --- | --- | NA |
| | | DEHP | --- | --- | NA |
| | | DIBP | --- | --- | NA |
| 3 | Black body | Pb | BL | --- | Pass |
| | | Cd | BL | --- | Pass |
| | | Hg | BL | --- | Pass |
| | | Cr(VI) | BL | --- | Pass |
| | | PBBS | IN | N.D. | Pass |
| | | PBDEs | IN | N.D. | Pass |
| | | DBP | --- | N.D. | Pass |
| | | BBP | --- | N.D. | Pass |
| | | DEHP | --- | N.D. | Pass |
| | | DIBP | --- | N.D. | Pass |

Test Report

Report No. : TCT260112C003008

Date : Jan. 20, 2026

Page No.: 3 of 6

Remark:

(1) EDXRF Screening test

- (a) It is the result on total Br while test item on restricted substances is PBBs/PBDEs. It is the result on total Cr while test item on restricted substances is Cr(VI).
- (b) Use the IEC62321-3-1:2013 method to perform EDXRF scanning screening on the sample. If the EDXRF result exceeds the screening limit, it is recommended that the customer use a more accurate chemical test method to test the sample

| Element | Polymer | Metal | Composite Materials |
|---------|--------------------------------|--------------------------------|--------------------------------|
| Cd | BL≤(70-3σ)<X< (130+3σ)≤OL | BL≤(70-3σ)<X< (130+3σ)≤OL | LOD<X<(150+3σ) ≤OL |
| Pb | BL≤(700-3σ)<X< (1300+3σ)≤OL | BL≤(700-3σ)<X< (1300+3σ)≤OL | BL≤(500-3σ)<X< (1500+3σ)≤OL |
| Hg | BL≤(700-3σ)<X< (1300+3σ)≤OL | BL≤(700-3σ)<X< (1300+3σ)≤OL | BL≤(500-3σ)<X< (1500+3σ)≤OL |
| Br | BL≤(300-3σ)<X | NA | BL≤(250-3σ)<X |
| Cr | BL≤(700-3σ)<X | BL≤(700-3σ)<X | BL≤(500-3σ)<X |

(c) BL = Below Limit, OL = Over Limit, IN = Inconclusive, LOD = Limit of Detection,
--- = Not Regulated, NA = Not Applicable.

(d) The EDXRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition.

(2) Chemical test

(a) 1mg/kg = 1ppm = 0.0001%, N.D.= Not Detected (<MDL), --- = Not Conducted.

(b) Chemical test limit and test method

The limit is quoted from RoHS directive 2011/65/EU and the amendment directive (EU) 2015/863.

| Test Item(s) | Test Method | Test Instrument | MDL | Limit |
|--------------|----------------------------|-----------------|-------------------------|------------|
| Pb | IEC 62321-5:2013 | ICP-OES | 10 mg/kg | 1000 mg/kg |
| Cd | IEC 62321-5:2013 | ICP-OES | 10 mg/kg | 100 mg/kg |
| Hg | IEC 62321-4:2013+AMD1:2017 | ICP-OES | 10 mg/kg | 1000 mg/kg |
| Cr(VI) | IEC 62321-7-1:2015 | UV-Vis | 0.10 µg/cm ² | - |
| | IEC 62321-7-2:2017 | UV-Vis | 10 mg/kg | 1000 mg/kg |
| PBBs | IEC 62321-6:2015 | GC-MS | Each 100 mg/kg | 1000 mg/kg |
| PBDEs | IEC 62321-6:2015 | GC-MS | Each 100 mg/kg | 1000 mg/kg |

Test Report

Report No. : TCT260112C003008

Date : Jan. 20, 2026

Page No.: 4 of 6

| | | | | |
|------|------------------|-------|-----------|------------|
| DBP | IEC 62321-8:2017 | GC-MS | 100 mg/kg | 1000 mg/kg |
| BBP | IEC 62321-8:2017 | GC-MS | 100 mg/kg | 1000 mg/kg |
| DEHP | IEC 62321-8:2017 | GC-MS | 100 mg/kg | 1000 mg/kg |
| DIBP | IEC 62321-8:2017 | GC-MS | 100 mg/kg | 1000 mg/kg |

(c) According to IEC 62321-7-1:2015, For metal samples,

- a. When the Cr (VI) concentration is $>$ the $0,13 \mu\text{g}/\text{cm}^2$, the sample is positive for Cr(VI) and considered to contain Cr(VI).
- b. When the Cr (VI) concentration is N.D. ($<$ the $0,10 \mu\text{g}/\text{cm}^2$), the sample is negative for Cr(VI) and considered a non-Cr(VI) based coating.
- c. When the Cr (VI) concentration is \geq the $0,10 \mu\text{g}/\text{cm}^2$ and \leq the $0,13 \mu\text{g}/\text{cm}^2$, the result is considered to be inconclusive - Unavoidable coating variations may influence the determination.

Because the storage condition and production date of the sample are not known, the test results of the sample of hexavalent chromium can only represent the state of hexavalent chromium in the samples tested.



Test Report

Report No. : TCT260112C003008

Date : Jan. 20, 2026

Page No.: 5 of 6

Photo(s) of the sample(s)




Test Report

Report No. : TCT260112C003008

Date : Jan. 20, 2026

Page No.: 6 of 6



*** End of Report ***

Remark: This report is considered invalidated without the Special Seal for Inspection of the TCT. This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of TCT, this test report shall not be copied except in full and published as advertisement.